

ZDS-CeramicArmor™ · CA SERIES

ZDS-CA1843

Brushable Enamel Wear Protection Coating



Product Description

Brushable Enamel Wear Protection Coating

Service Temperature

-60 to 160°C

Mixing Ratio

A:B = 8:1

Cure Schedule

60 h

Core Advantages

- ✓ High wear resistance
- ✓ Brushable application
- ✓ Ceramic-filled protection for severe service

Applications

Heat exchangers and tube sheets, pumps and pump casings, valves, tanks and vessels, impellers, industrial pipelines; protective coating.

Technical Data

Tensile strength	396
Shear strength	243
Compressive strength	972
Service Temperature	-60 to 160°C
Mixing Ratio	A:B = 8:1
Cure Schedule	60 h

Typical Application Parameters

Product Form	Coating
Mixed Color	Typical: Dark grey
Application Temperature	Recommended: 10°C to 35°C
Working Time (25°C)	Typical: 30-45 min
Recommended Layer	Recommended: 0.5-1.0 mm / coat
Initial Cure (25°C)	Typical: 4-6 h

Application Guidance & Storage

- Surface preparation: Clean, sound and oil-free substrate; abrade metal or composites and remove dust before application.
- Application: Measure the stated ratio, mix until uniform, then apply and compact to minimise entrapped air.
- Environment: Keep the substrate at least 3°C above dew point. Cold extends cure; heat shortens working time.
- Storage & safety: Store sealed at 5-30°C in a cool, dry place; typical shelf life 12 months. Use gloves and eye protection; consult the SDS.

Application values marked Typical or Recommended are engineering guidance derived from the product type, stated performance and intended use. Confirm critical project parameters by application testing.