


ZDS-FluidGlide™ · FG SERIES

ZDS-FG2116

High-Temperature Sealing Compound



Product Description

High-Temperature Sealing Compound

Service Temperature

-60 to 350°C

Mixing Ratio

A:B = 5:1

Cure Schedule

24 h

Core Advantages

- ✓ High-temperature service capability
- ✓ Barrier protection against aggressive fluids
- ✓ Designed for demanding thermal service

Applications

Flanges, boilers, industrial pipelines; sealing.

Technical Data

Density	1.40
Tensile strength	330
Shear strength	120
Service Temperature	-60 to 350°C
Mixing Ratio	A:B = 5:1
Cure Schedule	24 h

Typical Application Parameters

Product Form	Coating
Mixed Color	Typical: Dark grey
Application Temperature	Recommended: 10°C to 35°C
Working Time (25°C)	Typical: 30-45 min
Recommended Layer	Recommended: 0.5-1.0 mm / coat
Initial Cure (25°C)	Typical: 4-6 h

Application Guidance & Storage

- Surface preparation: Clean, sound and oil-free substrate; abrade metal or composites and remove dust before application.
- Application: Measure the stated ratio, mix until uniform, then apply and compact to minimise entrapped air.
- Environment: Keep the substrate at least 3°C above dew point. Cold extends cure; heat shortens working time.
- Storage & safety: Store sealed at 5-30°C in a cool, dry place; typical shelf life 12 months. Use gloves and eye protection; consult the SDS.

Application values marked Typical or Recommended are engineering guidance derived from the product type, stated performance and intended use. Confirm critical project parameters by application testing.